

TECHNICAL SHEET



Article: **B0241B MARGOT TOP**

Norm: **EN ISO 20345:11**

Safety Class: **S3 SRC**

Sole	S26 BLACK
Weight, size 42:	479 gr
Footwear height:	115 mm
Width:	10,5
Construction / Sole:	STROBEL; AirTech/Tpu-Skin injected outsole
Anti-perforation insert	Fresh'n Flex ballistic fabric
Insole:	
Footbed supplied:	Dry'n Air Gel
Other usable Footbeds (certified):	B07; Dry'n Air Omnia; Dry'n Air Scan&Fit Omnia; Secosol; Secosol Dynamic

Entire footwear: protections

Component	Description	Value	Minimum Requirement	Norm
Aluminium toe-cap	Impact resistance (200J)	15 mm	≥ 14 mm	5.3.2.3
	Compression resistance (15kN)	17,5 mm	≥ 14 mm	5.3.2.4
Outsole (SRC)	Slip resistance 20345:2011			
	•SRA – Hill (angle of 7°)	0,30	≥ 0,28	5.3.5.2
	•SRA – sole (full sole)	0,34	≥ 0,32	5.3.5.2
	•SRB – Hill (angle of 7°)	0,15	≥ 0,13	5.3.5.3
	•SRB – Sole (Full sole)	0,23	≥ 0,18	5.3.5.3
Fresh'n Flex (P)	Puncture resistance 20345:2011	No perforation	≥ 1100 N	5.2.1.1.2
Footwear with insole (A)	Antistatic properties			
	Electrical resistance	wet 233 MΩ- dry 91 MΩ	0,1 ÷ 1000 MΩ	6.2.2.2
Energy absorption (E)	Shock-absorption in the heel region	28 J	≥ 20 J	6.2.4

Upper

Materials	Description	Value	Minimum Requirement	Norm
Full grain waxy leather	Tear resistance	216 N	≥ 120 N	5.4.3
	Traction resistance	N/A	≥ 15 N/mm ²	5.4.4
	Water steam permeability	1,8 mg/cm ² h	≥ 0,8 mg/cm ² h	5.4.6
	Water steam coefficient	17,4 mg/cm ²	≥ 15mg/cm ²	5.4.6
	Chromium VI content (if leather)	Not detectable	Not detectable	6.11
	Water passed	0,0 g	≤ 0,2 g	6.3
	Water absorption	21 %	≤ 30%	6.3

Lining

Materials	Description	Value	Minimum Requirement	Norm
Hi-tech 3D fabric	Tear resistance	47 N	≥ 15 N	5.5.1
	Abrasion resistance	• No dry hole	No holes before 51,200 cycles	5.5.2
		• No hole in humid environment	No holes before 25,600 cycles	5.5.2
	Water steam permeability	21,1 mg/cm ² h	≥ 2,0 mg/cm ² h	5.5.3
Chromium VI content (if leather)	N/A	Not detectable	5.5.5	

Sole

Materials	Description	Value	Minimum Requirement	Norm
AirTech + Tpu-Skin anti-fatigue sole	Crampon height	2,7 mm	≥ 2,5 mm	5.8.1.3
	Tear resistance	7,2 kN/m	≥ 5 kN/m	5.8.2
	Abrasion resistance	81 mm ³	≤ 250 mm ³	5.8.3
	Flexural strength after 30,000 cycles	2,5 mm	≤ 4,0 mm	5.8.4
	Flexural strength after 150,000 cycles (hydrolysis)	3,0 mm	≤ 6,0 mm	5.8.5
	Tread-midsole detachment	N/A	> 4 N/mm; ≥ 3 N/mm with sole tear*	5.8.6
	Hydrocarbon resistance FO (volume change)	3,5 %	≤ 12%	6.4.2

Issued by: Innovation Director Ing. Cataldo De Luca

Signature



The content of this technical sheet is copyright of BASE PROTECTION Unipersonale Srl. Reproduction, even partial, of texts and / or images presented here is expressly forbidden.

Technical sheet subject to revision at the same time as the certificate is issued. Typographical errors excepted. BASE PROTECTION reserves the right to modify the content of the technical sheet.