

TECHNICAL SHEET

Article: B0993A PERSEUS

Norm: EN ISO 20345:2022

Safety Class: S3L SC FO SR

Sole	S29 BLACK
Weight, size 42:	585 gr
Footwear height:	135 mm
Width:	12
Construction / Sole:	STROBEL; single density AirTech injected outsole
Anti-perforation insert	Fresh'n Flex ballistic fabric
Insole:	
Footbed supplied:	Dry'n Air Omnia Comfort Plus
Other usable Footbeds (certified):	B07; Dry'n Air Gel; Dry'n Air Omnia; Dry'n Air Scan&Fit Omnia; Secosol; Secosol Dynamic



Entire footwear: protections

Component	Description	Value	Minimum Requirement	Norm
SlimCap toe-cap	Impact Resistance (200J)	15,0 mm	≥ 14,0 mm	5.3.2.3
	Compression Resistance (15 kN)	15,5 mm	≥14,0 mm	5.3.2.4
Outsole (SR)	Slip Resistance 20345:2022			
	•Ceramic + Det. - Heel	0,46	≥ 0,31	5.3.5.2
	•Ceramic + Det. + Forepart	0,40	≥ 0,36	5.3.5.2
	•Ceramic + Glycerin (SR) - Heel	0,22	≥ 0,19	6.2.10.1
Fresh'n Flex (PL)	•Ceramic + Glycerin (SR) - Forepart	0,25	≥ 0,22	6.2.10.1
	Puncture resistance. 20345:2022	No perforation	No perforation at ≥1100N	6.2.1.1.3
Footwear with insole (A)	Antistatic properties			
	Electrical resistance	dry 97,6 MΩ - wet 71,8 MΩ	0,1 ÷ 1000 MΩ	6.2.2.2
Energy absorption (E)	Shock-absorption in the heel region	32J	≥ 20 J	6.2.4
(SC)	•Abrasion resistance of the toe region	Comforms	After 8000 cycles, the SC has no holes	6.2.9

Upper

Materials	Description	Value	Minimum Requirement	Norm
Split leather	Tear Strenght	149 N	≥ 120 N	5.4.3
	Tensile Strenght	17 N/mm ²	≥ 15 N/mm ²	5.4.4
	Water vapour permeability	4,8 mg/cm ² h	≥ 0,8 mg/cm ² h	5.4.6
	Water vapour coefficient	40,3 mg/cm ²	≥ 15mg/cm ²	5.4.6
	Chromium VI content (if leather)	Not detectable	Not detectable	6.11
	Water passed	0,0 g	≤ 0,2 g	6.3
	Water absorption	10,4 %	≤ 30%	6.3

Lining

Materials	Description	Value	Minimum Requirement	Norm
Hi-tech 3D fabric	Tear Strenght	51 N	≥ 15 N	5.5.1
	Abrasion resistance	• No dry hole	No holes before 51,200 cycles	5.5.2
		• No hole in humid environment	No holes before 25,600 cycles	5.5.2
	Water steam permeability	80,1 mg/cm ² h	≥ 2,0 mg/cm ² h	5.5.3
	Chromium VI content (if leather)	N/A	Not detectable	5.5.5

Sole

Materials	Description	Value	Minimum Requirement	Norm
Single density AirTech outsole	Cleat height	4,6 mm	≥ 2,5 mm	5.8.1.3
	Tear Strenght	10,0 kN/m	≥ 5 kN/m	5.8.2
	Abrasion resistance	172 mm ³	≤ 250 mm ³	5.8.3
	Flexural resistance after 30,000 cycles	2,2 mm	≤ 4,0 mm	5.8.4
	Flexural resistance after 150,000 cycles (hydrolysis)	2,5 mm	≤ 6,0 mm	5.8.5
	Upper/outsole bond strenght	N/A	> 4 N/mm; ≥ 3 N/mm with sole tear*	5.8.6
	Hydrocarbon resistance FO (volume change)	4 %	≤ 12%	6.4.2

Issued by: Innovation Director Ing. Cataldo De Luca

Signature



The content of this technical sheet is copyright of BASE PROTECTION Unipersonale Srl. Reproduction, even partial, of texts and / or images presented here is expressly forbidden.

Technical sheet subject to revision at the same time as the certificate is issued. Typographical errors excepted. BASE PROTECTION reserves the right to modify the content of the technical sheet.